


What is claimed is:

1. A process for polymerizing an olefin comprising polymerizing or copolymerizing an olefin at a polymerization reaction temperature of 50 to 200 °C in the presence of an olefin polymerization catalyst comprising:

(A) a transition metal compound represented by the following formula (I),

(B-1) a compound having a reduction ability which reacts with the transition metal compound (A) to convert an imine structure moiety to a metal amide structure, and

(B-2) a compound which reacts with the transition metal compound (A) to form an ion pair;



wherein M is a transition metal atom of Groups 3 to 11 of the periodic table,

m is an integer of 1 to 6,

Y is an oxygen atom, a sulfur atom or a selenium atom, or a nitrogen atom having a substituent R⁷,

R¹ to R⁷ may be the same or different, they are each a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a nitrogen-containing group, a

boron-containing group, a sulfur-containing group, a phosphorus-containing group, a heterocyclic compound residual group, a silicon-containing group, a germanium-containing group or a tin-containing group, two or more of them may be bonded to each other to form a ring except for the case where R^1 and R^5 or R^1 and R^6 are bonded to each other to form an aromatic ring, and when m is 2 or greater, one group of R^1 to R^7 contained in one ligand and one group of R^1 to R^7 contained in other ligands may be bonded, and R^1 s, R^2 s, R^3 s, R^4 s, R^5 s, R^6 s and R^7 s may be the same or different,

n is a number satisfying a valence of M , and

X is a hydrogen atom, a halogen atom, a hydrocarbon group, an oxygen-containing group, a nitrogen-containing group, a boron-containing group, a sulfur-containing group, a phosphorus-containing group, a halogen-containing group, an aluminum-containing group, a heterocyclic compound residual group, a silicon-containing group, a germanium-containing group or a tin-containing group, and when n is 2 or greater, plural groups indicated by X may be the same or different, and plural groups indicated by X may be bonded to each other to form a ring.

2. The process for polymerizing an olefin as claimed in claim 1, wherein the transition metal compound

(A) is a compound in which R^4 in the above formula (I) is a halogen atom, a hydrocarbon group, an oxygen-containing group, a nitrogen-containing group, a boron-containing group, a sulfur-containing group, a phosphorus-containing group, a heterocyclic compound residual group, a silicon-containing group, a germanium-containing group or a tin-containing group.

3. The process for polymerizing an olefin as claimed in claim 1 or 2, wherein the olefin polymerization catalyst is a catalyst comprising the transition metal compound (A), the organic metal compound (B-1), the compound (B-2) which reacts with the transition metal compound (A) to form an ion pair, and a carrier (C).

4. The process for polymerizing an olefin as claimed in any one of claims 1 to 3, wherein the yield of polyolefin per 1 mol of a transition metal atom contained in the transition metal compound (A) and 1 hour of a polymerization time is 1000 kg or more.